PRODUCT DATA SHEET

Long term corrosion protection/sealing by Denso

DENSO 1750 SR/SA

Solar Reflective Waterproof Membrane

PRODUCT A self adhesive solar reflecting membrane designed for waterproofing applications for new or remedial roofing works not subjected to heavy traffic.

It incorporates all the characteristics and advantages of the Denso WPM products, but is aluminium foil faced to provide solar reflective protection.

It consists of an embossed aluminium foil laminated to a polymer modified bitumen and is available as Temperate and Tropical grades.

It is capable of handling elevated temperatures and is available in standard aluminium or colours to order.

The use of Solar Shield will assist in reducing structure temperatures by reflecting solar heat at the same time as providing waterproofing.

ADVANTAGES

- Factory controlled thickness
- Rapid sealing and bonding
- Fast and easy application
- Self sealing to minor damage
- Can also be used for flashing applications

For further detailing on installation, please refer to our Application Guide.

/2.... (Denso 1750 SR-SA)

The information on this sheet is intended as a general guide only and should not be used for specification purposes. We believe the information to be accurate and reliable but do not guarantee it. We assume no responsibility for the use of this information. Users must, by their own tests, determine the suitability of the products an information supplied by us for their own particular purposes. No patent liability can be assumed. In view of the constant research and development being undertaken in our laboratories, we advise customers in their own interests to ensure that this data sheet has not been superceded by a more up to date publication. All products are sold subject to the Standard Condition of Sale, copies of which are available on request.

DENSO 1750 SR/SA

TYPICAL DATA

Dimensions:

Backing Thickness: Backing Type:	0.08mm Embossed aluminium foil		
Total Thickness (nominal): Width: Length: Weight: Carton Size:	1,75mm 950mm 15m 2,m² 255mm x 255mm x 1100mm		
Carton Weight:	30kg		
Mechanical Properties: Tensile Strength: Elongation: Puncture Resistance: Adhesion (180°C Peel):	6.0 N/mm 20% 270 N 4.0 N/mm	ASTM D1000 ASTM D1000 ASTM E154 ASTM D1000	
Functional Data: Water Vapour Transm: Water Penetration Joint: Dimensional Stability: Longitudinal: Lateral: Application Temperature:	<0.1 g/m²/24h Nil % 0% 0% +5 to +35°C *	ASTM E96 MOAT 27/M5.1.4 MOAT 27/M5.1.6(80°C)	

Storage: Store in original containers in a cool, dry place. Maximum shelf life recommended: 6 months.



LEADERS IN CORROSION PREVENTION AND SEALING TECHNOLOGY

AND SEALING TECHNOLOGY								
				(Denso1750 SR-SA)			
FOR FURTHER INFO	RMATION PLEA	SE CONTACI	YOUR NEAREST	DENSO DEALER				
Natal (H/O)	Tel:	031 569-4319	Fax:	031 569-4328				
Gauteng		011 674-5412		011 674-3956				
Cape		021 903 6063		021 906 2310				
E. Cape		041 365-2711		041 365-2715				
Namibia		09264 61 219	606	09264 61 219616				
E-Mail / Website:		bid@denso.co	o.za	www.denso.co.za				